



## Clear Grip 70g/m<sup>2</sup> (50µm)

	TESTS	NORM	UNIT	SM/ST	MAIN VALUE	DEVIATION
<b>TEXTURE</b>	Weight	NFT 54-101	g/m <sup>2</sup>		96,4	0,4
	Thickness		µm		167,7	4,8
	Density (23°C)	ASTM D. 1505	g/cm <sup>3</sup>		1,395	
<b>MECHANICAL PROPERTIES</b>	Breaking strength in traction	ASTM D.882	daN/mm <sup>2</sup>		20	
	Elongation		%		140	
<b>AIR/WATER POROSITY</b>	Cobb 60s.	T441-OM98	g/m <sup>2</sup>	recto	10	
			g/m <sup>2</sup>	verso	10	
<b>FRICITION</b>	Static friction coefficient	ISO 8295		SM	0,99	0,09
	Sliding angle		°	SM	44,7	
<b>HEALTH</b>	Toxicity				none	
	Skin irritation				none	
	Food contact aptitude	Reg. N°CE 1935/2004			Exemption of food contact aptitude in normal conditions of use	
<b>ENVIRONMENT</b>	Reuse	NF 13429			yes	
	Content of recycled	measured	%		0	